


# Reliability for Acriche – Pure white




<L70 Lifetime>

$T_j=80^\circ\text{C}$  40,000hr

$T_j=90^\circ\text{C}$  30,000hr

$T_j=100^\circ\text{C}$  22,000hr

# Reliability for Acriche – Warm white



<L70 Lifetime>

$T_j=80^\circ\text{C}$  30,000hr

$T_j=90^\circ\text{C}$  20,000hr

$T_j=100^\circ\text{C}$  15,000hr